



**PROTECTIVE
&
MARINE
COATINGS**

**FasTop RS69 SP
PRODUCT TECHNICAL DATA**



PRODUCT DESCRIPTION

FasTop RS69 SP is a heavy duty resin rich polyurethane concrete floor screed that has excellent resistance to a wide variety of chemicals and temperatures up to 120°C. FasTop RS69 SP can be applied by rake and trowel enabling fast installation to provide anti-slip surfaces suitable for use in a variety of wet and dry environments which are impervious and resistant to abrasion and heavy impacts. The properties of FasTop RS69 SP make it ideal for applications in the food and beverage, chemical and pharmaceutical industries to provide a durable, long lasting floor.

ADVANTAGES

- High chemical resistance
- Resistant to hot water and steam
- Resin rich and self sealing
- Extremely hard wearing
- Excellent slip resistant finish
- Matt finish
- HACCP certified

RECOMMENDED USE

- Food manufacture and processing
- Brewing and beverage
- Pharmaceutical and chemical plant processing
- Heavy duty plant and traffic areas
- Dairies
- Commercial kitchens
- Abattoirs and meat processing

PRODUCT DATA

Volume Solids:	~100%	Application at 20°C	
Finish:	Matt finish	Recoating Intervals:	N/A
Flash Point:	N/A	Light Traffic:	12-16 hours
Cleanser/Thinner:	N/A	Full Traffic:	48 hours
Pack Size:	25.3 kg	Full Chemical Cure	5-7 days
Pack Weights:	2.5 kg Blank base 2.5 kg Hardener 0.3 kg Colour pack 20 kg Aggregate	Pot Life:	15 minutes from mixing
Mixing Ratio:	As above packing weights	Note: All mixed paint must be used within the pot life time limit, if the paint is left in the container after mixing and not used, it may release hazardous fumes due to exothermic reaction.	
Shelf Life:	All resin components have a 12 month shelf life when kept in unopened containers. Aggregates have a 6 month shelf life stored in good conditions.	Coverage Rate:	25.3 kg will cover 2.1 m ² @ 6 mm or 1.4 m ² @ 9 mm (or 2 kg/m ² per mm) (Theoretical) Coverage rate is calculated based on a sealed and smooth surface and may vary based on the substrate roughness and other conditions.
Storage:	Keep out of direct sunlight. Store in a dry place, between 15°C – 30°C. Aggregates must be stored in a dry area to prevent contamination by moisture, as this will have a detrimental effect on the product.	System Thickness: (Recommended)	6-9 mm
		<i>The suggested thickness range is calculated based on average volume solid as a general recommendation for the specified condition and for each application may vary.</i>	
		Recommended Application Methods:	Trowel/rake with optional finish with a roller



FasTop RS69 SP

SURFACE PREPARATION

New Concrete Floors: New concrete must be clean, sound, dry, fully cured and surface laitance removed by vacuum enclosed shot blasting or mechanical grinding, a minimum strength of 25 N/mm² is required.

Existing Concrete Floors: Remove all dirt, oil, grease, old paint or any other surface contaminants by vacuum enclosed shot blasting, scarifying or mechanical grinding. Fats, oils or greases must be removed by mechanical means and detergent washing and making sure all residue of detergent is washed and removed by rinsing with clean water. Local repairs should be carried out using **FasTop BU SP**.

Existing Floors (previously coated): All previous coatings and loose floor paints must be removed by mechanical preparation as described in the above section and primed as specified. If the old resin flooring cannot be removed then please consult with our technical team for advice on intercoat adhesion and suitability, as it may not be compatible with the existing floor coating.

Anchor Joints: To ensure the maximum bond is achieved, grooves must be cut into the perimeter of the subfloor, typically 20 mm deep by 10 mm wide. These should be inset approximately 150 mm from and running parallel with the walls and adjacent to any doorways, plinths etc. including any finished edge, i.e. both sides of a day work joint. The groove must have a neat square edge and the **FasTop RS69 SP** laid to the full depth forming a perimeter anchorage.

APPLICATION

4-pack Mixing: Add the **FasTop Multi SP** blank base **Part A** pouch and then the **FasTop Multi SP** colour pack pouch contents into a mixing bucket or directly into a rotary drum mixer, mix thoroughly for one minute then add the **FasTop Multi SP** hardener **Part B** pouch component. If a separate bucket has been used pour the combined mix into a rotary drum mixer and add the **FasTop RS69 SP** aggregate component steadily, until a homogeneous mix of the four components is achieved.

Apply immediately to prepared areas. When priming a surface this should be tack free and **FasTop RS69 SP** should be applied at the required rate as soon after mixing as possible. Level between battens as necessary with a steel float, alternatively a sledge can be used set at the required thickness and again finished with a steel float. Where ease of cleaning is very important alongside slip resistance, the final finish can be smoothed by back rolling with a short nap roller. A single pass with the weight of the roller is usually sufficient. Delay can result in variation in surface finish, colour and add to application problems.

FasTop RS69 SP may be applied to substrates with a surface temperature in the range of 5-20°C and a relative humidity <90% RH, with a minimum air temperature of 8°C and no condensation. Do not pre-warm this product as working times will be substantially reduced if materials are warm.

NB: Cure times are extended at low temperatures.

RECOMMENDED PRIMING

Dry or porous substrates can be primed using **FasTop TC** where the relative humidity of the substrate is less than 75%. This should be lightly scattered with silica aggregate approximately 1 mm in size. Where the Relative Humidity of a substrate exceeds 75% ERH **Resuprime MVT** should be specified and selected on the basis of hygrometer readings in accordance with BS 8203. The number of coats to be applied is chosen in accordance with the following table:

ERH%	Required Coating Thickness
75-85	1 coat of Resuprime MVT at 200 µm per coat
85-92	2 coats of Resuprime MVT at 200 µm per coat
92-97	3 coats of Resuprime MVT at 200 µm per coat

For further information please refer to recommended individual product data sheets.

WARRANTY

Any person or company using the product without first making further enquiries as to the suitability of the product for the intended purpose does so at their own risk, and Sherwin-Williams can accept no liability for the performance of the product, or for any loss or damage arising out of such use.
The information detailed in this datasheet is liable to modification from time to time in the light of experience and normal product development, and before using, customers are advised to check with Sherwin-Williams, quoting the reference number, to ensure that they possess the latest issue.

DISCLAIMER

The information and recommendations set forth in this Product Data Sheet are based upon tests conducted by or on behalf of The Sherwin-Williams Company. Such information and recommendations set forth herein are subject to change and pertain to the product offered at the time of publication. Consult your Sherwin-Williams representative to obtain the most recent Product Data Information and Application Bulletin.

HEALTH AND SAFETY

Consult Product Health and Safety Datasheet for information on safe storage, handling and application of this product.

Sherwin-Williams Protective & Marine Coatings, Tower Works, Kestor Street, Bolton, Lancashire BL2 2AL United Kingdom

T: 01204 521 771 E: sales.uk@sherwin.com www.resinflooring.sherwin.eu

Registered in England 1659941 VAT GB 373 485624

This datasheet is specifically subject to the disclaimer which can be found at: <http://protectiveemea.sherwin-williams.com/Home/Disclaimer>